



Technical Datasheet HOLDIT AUSTRALIA G51

Revised Date: MARCH 2020

Description

HOLDIT AUSTRALIA G51 Gasket Maker is a single component medium strength, Thixotropic, anaerobic sealant which cures when confined between close fitting metal surfaces. G51 Gasket Maker provides an instant low pressure seal.

Applications

HOLDIT AUSTRALIA G51 seals joints between rigid metal faces and flanges such as valve covers and gearbox castings. This product can be used with or without pre-cut, pre-formed gaskets.

Instructions for Use

1. For best results clean all surfaces with a cleaning solvent and allow to dry.
2. If the metal is inactive or the cure speed is too slow apply HOLDIT AUSTRALIA AA471 Standard Anaerobic Activator. Please see table below for information on Active and Inactive metals.
3. Before application knead the product thoroughly.
4. Normally hand applied from bottle onto parts.
5. Assemble components, and tighten to require torque level.
6. Allow to fully cure before applying load.

Properties of Uncured Material.

Resin	Polyethylene Glycol Dimethacrylate
Colour	Pink paste
Viscosity @ 25°C	100,000-500,000 cps

Performance of Cured Material

Fixture Speed without Primer	90 Minutes @ 25°C
Full Cure	24 Hours @ 20°C
Shear Strength	6-10 N/mm ²
Gap Fill	.3mm
Temperature Range	-53°C to 148°C

Retained Strength

100°C	50%
135°C	25%
150°C	20%

Compatible Primers

Primer such as HOLDIT AUSTRALIA AA649 Accelerator and HOLDIT AUSTRALIA AA471 Activator can be used to speed the fixture time of the adhesive. Fixtures times can improve by as much as 50%. The use of primers can result in lower strength and performance and should be tested after full cure.

ACTIVE & INACTIVE METAL TABLE

Super Active Very Fast Cure	Active Fast Cure	Inactive Slow Cure	Passive Primer Necessary
Brass, Copper, Magnesium	Iron, Steel, Nickel, Aluminium	Stainless Steel, Titanium, Zinc, Anodized Aluminium, Galvanised Steel	Ceramics, Glass, Plastics, Painted Finishes



Technical Datasheet HOLDIT AUSTRALIA G51

Revised Date: MARCH 2020

Storage

HOLDIT AUSTRALIA G51 should be stored in a dry cool area, out of direct sunlight. Optimal Storage temperature: 8-10C to 30°C.

Presentation

HOLDIT AUSTRALIA G51 is available in 50ml and 250ml Tubes.

Note

Where gap size is large or where the surface is uneven, apply primer to help cure the product through volume. G51 can be roller coated, screen printed or applied by pads.

Health & Safety in Use

IRRITANT: Contains Methacrylate Esters which may irritate eyes, respiratory organs and skin. In case of contact with the skin, wash immediately with plenty of water.

Conversions

- $(^{\circ}\text{C} \times 1.8) + 32 = ^{\circ}\text{F}$
- $\text{N/mm} \times 5.71 = \text{lb/in}$
- $\text{MPa} \times 145 = \text{psi}$
- $\text{N/mm}^2 \times 145 = \text{psi}$
- $\text{N} \times 0.225 = \text{lb}$
- $\text{N}\cdot\text{m} \times 8.851 = \text{lb}\cdot\text{in}$
- $\text{N}\cdot\text{mm} \times 0.738 = \text{lb}\cdot\text{ft}$
- $\text{mPa}\cdot\text{s} = \text{cP}$

ACTIVE & INACTIVE METAL TABLE

Super Active Very Fast Cure	Active Fast Cure	Inactive Slow Cure	Passive Primer Necessary
Brass, Copper, Magnesium	Iron, Steel, Nickel, Aluminium	Stainless Steel, Titanium, Zinc, Anodized Aluminium, Galvanised Steel	Ceramics, Glass, Plastics, Painted Finishes

The information contained herein is produced in good faith and is believed to be reliable but is for guidance only. Holdit Australia Pty Ltd and its agents cannot assume liability or responsibility for results obtained in the use of its products by persons whose methods are outside or beyond our control. It is the users responsibility to determine the suitability of any of the products and methods of use or preparation prior to use mentioned in our literature and furthermore the users responsibility to observe and adopt such precautions as may be advisable for the protection of personnel and property in the handling and use of any of our products. **PAGE 2 OF 2**